

PRODUCTION OF LOW ALPHA-OLEFIN POLYMER

Patent number: JP8283332
Publication date: 1996-10-29
Inventor: ARAKI YOSHITAKE; NAKAMURA HIROFUMI;
ISHIKAWA KYO; TSUBOI AKIO
Applicant: MITSUBISHI CHEM CORP
Classification:
- **international:** C08F4/69; C08F2/06; C08F6/06; C08F6/08; C08F10/00
- **european:**
Application number: JP19950092604 19950418
Priority number(s): JP19950092604 19950418

Abstract of JP8283332

PURPOSE: To obtain an improved process for producing a low α -olefin polymer in the presence of a chromium catalyst, the process having been improved so that a by-product polymer and the catalyst component can be efficiently removed, enabling the low α -olefin polymer to be produced industrially advantageously. **CONSTITUTION:** A low polymn. of an α -olefin is conducted in a solvent in the presence of a catalyst system at least comprising a chromium compd., at least one compd. selected from among an amine, an amide, and an imide, and an alkylaluminum compd. Then, after a by-product polymer is precipitated, separated, and removed from the reaction soln, the catalyst component is condensed and separated at the step of separation by distillation.

Data supplied from the **esp@cenet** database - Worldwide